

Sealer Mikon® 398 MC

page: 1 / 1
 revision: 19.03.2019
 author: MM / sde
 print: 19.03.2019

Description:

Sealer Mikon® 398 MC is a specially designed surface sealer for porous surfaces to seal them with a high quality finish. The sealer convinces with its simple application. If handled properly, there will be no need to sand nor to polish. Compared to our Sealer Mikon® 399 MC, Sealer Mikon® 398 MC exhibits a lower viscosity.

Application Fields:

Sealing of porous surfaces, especially block materials, MDF and plastic as well as metal moulds. It can also be used for reprocessing surfaces of polyester or epoxy resin.

Application:

Sealer Mikon® 398 MC is ready-to-use and should not be diluted. The surface to be sealed must be absolutely dustfree and free of grease residues. Optimal results are obtained by applying the sealer with a suitable lint-free cotton cloth. Depending on the porosity of the surface, repeat until the desired surface quality has been achieved. Usually, 2 or 3 coatings with an eventual sanding using an abrasive fleece are sufficient. After each application a curing time of minimum 30 minutes at a room temperature of approx. 20°C/68°F should be respected. Only very thin layers of Sealer Mikon® 398 MC must be applied as too thick layers tend to crack. For best release performance, we strongly recommend subsequent application of any semi-permanent release agent from our Mikon® series. Both water- and solvent-based release agents will be adequate. Application equipment (brush or similar) should be thoroughly cleaned immediately from liquid residues using a suitable solvent, for example, Mikon® Cleaner R-47. Cured Sealer Mikon® 398 MC can only be mechanically cleaned / removed.

Technical Data

Composition:	resin solution
Appearance:	clear liquid
Density [g/cm³]:	approx. 0,90
Flashpoint [°C]:	-1

Packaging:

bottle 0,9 kg

Storage:

This product should be stored in tightly sealed containers and has to be protected from frost, heat and direct sunlight. If these rules are obeyed, the product can be stored for at least 24 months. The expiry date is stated beneath the production date on the labels of each container.

Regulatory information on safety and transportation is provided in the material safety data sheet.

Technical product information and data is based on the best information available and does not constitute or imply a warranty or patent infringement of any kind. The user is responsible for testing product suitability prior to product use in production. The data mentioned above do not constitute viable parts of a specification, for which further, separate agreements are necessary.



Management
 System
 ISO 9001:2015
 ISO 14001:2015
 www.tuv.com
 ID 9105031335

Viernheimer Str. 70-76
 D-69469 Weinheim
 Postfach 10 07 29
 D-69447 Weinheim
 Geschäftsführer:
 Wilhelm Münch, Michael Münch
 Amtsgericht Mannheim HRB 431102

Tel +49 6201 - 9983 0
 Fax +49 6201 - 9983 66
 info@muench-chemie.com
 www.muench-chemie.com
 USt.-IDNr. DE144497299
 Steuer-Nr. 47020 / 10016

Bankverbindungen

Deutsche Bank AG
 BLZ 670 700 24
 Kto. 586 896 300
 Swift Code/BIC: DEUT DE DB MAN
 IBAN: DE84 6707 0024 0586 8963 00

Volksbank eG
 BLZ 670 923 00
 Kto. 1 078 801
 Swift Code/BIC: GENO DE 61 WNM
 IBAN: DE40 6709 2300 0001 0788 01