

*Valvoline Performance Products – Tectyl*

Version: TE017/01

## Tectyl™ 122-A

*Premium wax/asphaltic based, corrosion preventive underbody coating.*

**TECTYL 122-A** is a solvent cutback wax/asphaltic base, thixotropic corrosion preventive compound.

**TECTYL 122-A** is suitable to be applied to the undersides of vehicles.

**TECTYL 122-A** dries to a relatively firm, black, resilient, tough film.

### Approvals/Performance levels

<b>Tectyl 122-A</b>
<b>Accelerated Corrosion tests:</b> @ Average recommended DFT
<b>Accelerated Corrosion tests:</b> Salt Spray; 5 % NaCl @ 35°C; ISO 9227 NSS (Q-Panels, Type R, ASTM A1008) <b>40+ days</b>
Humidity; 100 % RH; @ 40°C; ISO 6270-2 CH (Q-Panels, Type R, ASTM A1008) <b>100+ days</b>
<b>Estimated Protection Period</b>
Indoor: 36 months Outdoor: 21 months

### Application

**Preparation:**

The maximum performance of **TECTYL 122-A** can be achieved only when the metal surfaces to be protected are clean, dry and free of rust, oil and mill scale. Avoid direct contact of the product with PVC due to possible material incompatibility.

**Application:**

**TECTYL 122-A** is formulated to be used as supplied. It is recommended that the ambient and product temperature be 10-35 °C at the time of product application. **TECTYL 122-A** can be applied by airless spray or brush.

**Removal:**

**TECTYL 122-A** can be removed with mineral spirits or any similar petroleum solvent, vapor degreasing, hot alkaline wash or low pressure steam. Also Tectyl Biocleaner can be used to remove Tectyl 122-A.

### Features and Benefits

**Protection at high temperatures**

Tectyl 122-A is very suitable as a protective coating in areas where high temperatures in combination with periods under the dew point occur.

**Multi functional**

Tectyl 122-A can be applied on many different vehicles, such as cars, trucks, busses, campers and construction equipment, but also trailers and caravans.

**Processing**

Tectyl 122-A is an easy to apply, elastic, protective underbody coating.

**Multiple substrates**

The underbody coating can also be used on different substrates, such as the wooden underside of a camper or caravan.

**Health and Safety**

For the health and safety related properties of this product reference is made to the Safety Data Sheet (SDS). A Safety Data Sheet is available on request via your local sales office or via the internet @ <http://msds.ashland.com>

**Protect the Environment**

Do not discharge into drains, soil or water.

**Storage**

Tectyl 122-A should be stored at temperatures between 10-35 °C. Mild agitation is recommended prior to use. Due to its composition Tectyl 122-A can be subject to postproduction viscosity changes during storage. Under proper storage conditions Tectyl 122-A can have a shelf life of 36 months minimum.

**Typical Properties**

Typical property characteristics are based on current production. Whilst future production will conform to Tectyl specifications, variations in these characteristics may occur.

<b>Tectyl 122-A</b>	
<b>Flash Point, PMCC [°C]</b>	40
<b>Density @ 20°C [kg/ltr]</b>	0,91
<b>Recommended Dry Film Thickness over metal profile [microns]</b>	250
<b>Theoretical coverage @ recommended DFT [m²/ltr]</b>	2,1
<b>Non Volatile [weight %]</b>	60
<b>Viscosity; Brookfield @ 25°C</b>	
@ 2 RPM mPa.s [cP]	25.000
@ 20 RPM mPa.s [cP]	8.000
<b>Dry to touch time @ 20°C [hours]</b>	4
<b>Cure time @ 20°C [hours]</b>	24
<b>Volatile Organic Content ISO 11890-2 (10.4) [g/ltr]</b>	358

**This information only applies to products manufactured in the following location(s):  
Europe**

**Trusted since 1930**

Since 1930, Tectyl™ protective coatings have been extending the operational life of cars, trucks, buses and other vehicles and equipment. The Tectyl name is synonymous with quality coatings that are easy to apply, long-lasting and easy to remove when no longer required.

For more information on Tectyl products, programs and services please visit [www.tectyl-europe.com](http://www.tectyl-europe.com)

**Caution**

Adequate ventilation is required for cure and to ensure against formation of combustible liquid. THE PARTIALLY CURED FILM SHOULD NOT BE EXPOSED TO IGNITION SOURCES SUCH AS FLARES, FLAMES, SPARKS, EXCESSIVE HEAT OR TORCHES. Refer to the Material Safety Data Sheet for additional handling and first aid information.

**Note**

The addition of any product over or under this coating is not recommended. The use of additional coatings could result in chemical incompatibility, thus affecting the performance of this coating as stated in the Typical Properties section. When applied on top or under another layer, please test prior to use on a small surface.

**Author:**

RdB, June 2015

Replaces March 2006

\*Trademark owned by a third party ™ Trademark of Ashland or its subsidiaries, registered in various countries © 2016, Ashland

All statements, information and data presented herein are believed to be accurate and reliable, but are not to be taken as a guarantee, an express warranty, or an implied warranty of merchantability or fitness for a particular purpose, or representation, express or implied, for which Ashland Inc. and its subsidiaries assume legal responsibility.